


Aspanger non-milled Aspolit

Aspanger non-milled Aspolit is a special, more-component filler, mainly consisting of Muscovite Mica and Quartz from our own Austrian deposit. Aspanger non-milled Aspolit is available in semi-moist or dried form. More details you can find under www.aspanger.com

General Characteristics	Specific Gravity (g/cm ³) ISO 787/10-1981	2,75
	pH ISO 787/9-1981	9,5
Chemical Analysis	SiO ₂	69,0 %
	Al ₂ O ₃	15,5 %
	K ₂ O	6,5 %
	CaO	0,5 %
	Fe ₂ O ₃	2,0 %
	MgO	2,8 %
	TiO ₂	0,5 %
	P ₂ O ₅	0,2 %
	Loss on ignition	2,0 %
Particle Size Mastersizer 3000E	98%	160,0 μm
	90%	120,0 μm
	50%	52,0 μm
	30%	35,0 μm



Technical information and data described herein are believed to be reliable but should not be taken as a specification and cannot establish any liability!

REV 5/10-2023