

# Aspolit W 75 - 80

Aspanger Aspolit is a special more-component filler, mainly consisting of Muscovite-MICA and quartz. The functional filler is 100% produced from our own Austrian deposit only 70 km south of Vienna, which will last for more than 100 years. More details you can find under [www.aspanger.com](http://www.aspanger.com)

General Characteristics	Specific Gravity (g/cm <sup>3</sup> ) ISO 787/10-1981	2,75
	Moh's Hardness MICA	2,5
	Moh's Hardness Quartz DIN-EN-15771	7
	Whiteness FMY (%) ISO 2470	75
	Humidity (%) ISO 787/2-1981	<1
	pH ISO 787/9-1981	9,5
	Oil Adsorption (g/100g) ISO 787/5-1980	13
Loose Bulk Density (g/l) DIN ISO 697	760	
Chemical Analysis	SiO <sub>2</sub>	71 %
	Al <sub>2</sub> O <sub>3</sub>	15 %
	K <sub>2</sub> O	6 %
	CaO	0,3 %
	Fe <sub>2</sub> O <sub>3</sub>	2 %
	MgO	2 %
	TiO <sub>2</sub>	0,3 %
	Na <sub>2</sub> O	0,1 %
	P <sub>2</sub> O <sub>5</sub>	0,1 %
LOI at 600°C	<2,00 %	




## Aspolit W 75 - 80

Particle Size  
 Distribution  
 Sedigraph 5120 /  
 Mastersizer 3000E

d98  
 d90  
 d50  
 d30

80,0  $\mu\text{m}$  / 125,0  $\mu\text{m}$   
 40,0  $\mu\text{m}$  / 80,0  $\mu\text{m}$   
 18,0  $\mu\text{m}$  / 26,0  $\mu\text{m}$   
 12,0  $\mu\text{m}$  / 14,5  $\mu\text{m}$



Technical information and data described herein are believed to be reliable but should not be taken as a specification and cannot establish any liability!

REV 3/02-2023